



Unit E, 3 Tudor Road, Altrincham Business Park, Cheshire, WA14 5RZ
 Tel : 0161 975 9002 Email : sales@friedmans.co.uk Web : www.friedmans.co.uk

Technical Data Sheet

Article	PF1006 Affinity White Polyester		
Composition	100% POLYESTER 47% Polyester P.B.T. + 53% Polyester		
Weight m ²	170 g/m²		
Total width (+/- 3 cm)	160 cm		
Weight linear m.	272 g/m lin.		
Dimensional Stability – Washing 40° C BS EN ISO 6330 – flat dry	width -4% MAX	length -4% MAX	
Dimensional Stability – Steam	width -4% MAX	length -4% MAX	
Resistance to pilling NU Martindale – ISO 12945-2 7.000 rotations	on fabric	5	on wool 4
Ultraviolet Protection Factor (U.P.F) AS/NZS 4399-1996	50+		
Hand Elongation (+/- 10%)	width 110% (min 99% - max 121%)	length 80% (min 72% - max 83%)	
Stretch to Dynamometer (+/- 10%) INSTRON 3343 – load 3.6 kg - strip test - size of the tested sample: 100 mm x 50 mm.			
White for printing	width 105% (min 94% - max 116%)	length 75% (min 67% - max 71%)	
Ultraviolet Protection Factor (ref. standard AS/NZS 4399:2017)	50+		

Care labelling codes:     




Chlorine Proof



Shape Retention



Pilling Resistant



Breathable



Perfect Fit



Excellent UV
Protection



Two-way Stretch

Notes:

Technical Specification details prior to a print or foil application.

Please note due to the numerous different Industries we supply, we cannot perform tests to everyone's requirement therefore we strongly recommend you carry out your own tests.

We recommend testing each dyebath before any treatment or application other than cutting and sewing. To improve our products, we reserve to modify these, as and when necessary.