

Unit E, 3 Tudor Road, Altrincham Business Park, Cheshire, WA14 5RZ Tel: 0161 975 9002 Email: sales@friedmans.co.uk Web: www.friedmans.co.uk

## Technical Data Sheet

Article **PF1010 PEACH POLYESTER** 

Composition **81% POLYESTER 19% ELASTANE** 

200 g/m<sup>2</sup> Weight m<sup>2</sup> (+/- 5%)

Weight linear m. (+/- 5%) 300 g/m lin. Total width (+/- 2%) 150 cm

Dimensional Stability - Washing 40° C - flat dry width -6% MAX length -6% MAX **BS EN ISO 6330** 

Dimensional Stability - Steam width -4% MAX length -4% MAX

Resistance to pilling on fabric 4/5 on wool 4

NU Martindale – ISO 12945-2 7000 rotations

Hand Elongation (+/- 15%) width 115% length 135%

(min 98% - max 132%) (min 115% - max 155%)

Stretch to Dynamometer (+/- 15%) INSTRON 3343 - load 3.6 kg - strip test - size of the tested sample: 100 mm x 50 mm

> Plain dyed width 110% length 130% (min 94% - max 127%) (min 111% - max 150%)

Modulus 40% Plain dyed width 155-290g length 150-280g

40/ A P











**UV Protection** 



4 Way Stretch



Shape Retention



## Notes:

Technical Specification details prior to a print or foil application.

Please note due to the numerous different Industries we supply, we cannot perform tests to everyone's requirement therefore we strongly recommend you carry out your own tests

We recommend testing each dyebath before any treatment or application other than cutting and sewing. To improve our products, we reserve to modify these, as and when necessary.