



Unit E, 3 Tudor Road, Altrincham Business Park, Cheshire, WA14 5RZ
 Tel : 0161 975 9002 Email : sales@friedmans.co.uk Web : www.friedmans.co.uk

Technical Data Sheet

Article	Supplex	
Composition	88% POLYAMIDE 12% ELASTANE	
Weight m ² (+/- 5%)	230 g/m²	
Weight linear m.	356 g/m lin.	
Total width (+/- 5%)	155 cm	
Dimensional Stability – Washing 40° C BS EN ISO 6330	width -5% MAX	length -5% MAX
Stretch to Dynamometer (+/- 10%) ZWICK – 1.5kg	width 130% (min 117%-143%)	length 90% (min 81% - 99%)
Modulus 40%	width 65-125g	length 95-185g
Resistance to pilling NU Martindale – ISO 12945-2 7.000 rotations	on fabric 2/3	on wool 2
Ultraviolet Protection Factor (U.P.F) AS/NZS 4399-1996	50+	

Care labelling codes:



Muscle Control



Excellent UV Protection



Two Way Stretch



Perfect Fit



Soft



Breathable



Extra Comfort

Notes:

Technical Specification details prior to a print or foil application.

Please note due to the numerous different Industries we supply, we cannot perform tests to everyone's requirement therefore we strongly recommend you carry out your own tests

We recommend testing each dyebath before any treatment or application other than cutting and sewing. To improve our products, we reserve to modify these, as and when necessary.